

Appendix: Weathering Data on TPU 2058

General: The below color was tested at QUV equipment with the following details:

Standard: ASTM G- 154, UVA

Test Cycle: UVA – 8 hrs. 60°c, 4 hrs. Cond. 50°c

Color	0 ÷ 1000 hr.	1000 ÷ 2000 hr.	2000 ÷ 3000 hr.
Orange	A	A-B	B

Legend

- A- No Change
- B- Minor Change
- C- Major Change

Remarks: There isn't direct correlation between QUV hours and years at service.

Our best evaluation is as follows:

- 1000 hrs. At QUV is estimate as 1 year in field service.
- 2000 hrs. At QUV is estimate as 1.5- 2 years in field service.
- 3000 hrs. At QUV is estimate as 2.5- 3 years in field service.